


Fabreeka®-PTFE Bearing Pads



Fabreeka-PTFE bearing pads are manufactured using Fabreeka pad material with a Teflon® (PTFE) surface. The virgin Teflon is heat cured to the Fabreeka pad using a rigid, laminated thermoplastic (LTP). The rigid LTP layer prevents the PTFE from expanding/flowing under compressive load and rotation (also known as "cold flow"), as the bearing pad compresses.



Fabreeka-PTFE bearing pads are used for conditions where it is necessary to accommodate lateral movement (expansion). The PTFE provides a low friction sliding surface on the Fabreeka bearing pad, which distributes high compressive loads and accommodates rotations. In a structural bearing design, polished stainless steel is typically used as the smooth surface that the PTFE slides against.

Features and Attributes

- Commonly used in structural expansion bearings and pipe slides
- Bearing pad meets AASHTO 18.4.9.1, MIL-C-882 and most state DOT specifications
- PTFE (Teflon) surface provides low friction for expansion
- Accommodates lateral movement and rotation
- Allows for rotations up to 0.02 radians under high pressure

Physical Properties


<u>PROPERTY</u>	<u>TEST</u>	<u>SPECIFICATION</u>
<i>Hardness at 78°:</i>	ASTM D2240	50-65 Durometer D
<i>Tensile Strength:</i>	ASTM D4894/4895	2,800 psi (min)
<i>Elongation:</i>	ASTM D4894/4895	200% (min)
<i>Deformation under Load:</i> 78°F - 2,000 psi (1/2" x 1/2" x 1/32")	ASTM D621	4% (max)
<i>Specific Gravity:</i>	ASTM D792	2.14 to 2.21

Note: Please refer to the Fabreeka Bearing Pad specification sheet #1000-005 for the physical properties of the Fabreeka pad.

Specification for Fabreeka®-PTFE Bearing Pads

The *bearing pad* shall be manufactured of all new (unused) materials and composed of multiple layers of prestressed 50/50 cotton-polyester blend duck, 8.1 ounce per net square yard, duck warp count 50 ± 1 threads per inch and filling count 40 ± 2 threads per inch, impregnated and bound with a high quality, oil-impervious nitrile rubber compound, containing rot and mildew inhibitors and anti-oxidants, compounded into resilient pads of uniform thickness. The pads shall withstand compressive loads perpendicular to the plane of laminations of not less than 10,000 psi before breakdown.


The *Polytetrafluorethylene (PTFE)* self-lubricating surface element shall be composed of 100 percent virgin (unfilled) polytetrafluorethylene polymer and bonded to a rigid confining substrate. The substrate shall limit the flow (elongation) of the confined PTFE to not more than 0.009" under load of 2,000 psi for 15 minutes at 78°F for a 2" x 3" test sample. The virgin (unfilled) PTFE shall have a thickness of not less than 1/32".




Additional Products for Building & Construction




SA-47 Bearing Pads



Fabreeka Bearing Pads
AASHTO 18.4.9.1



Structural Expansion Bearings



Flexible Drain Trough

If you have any questions regarding how Fabreeka's products comply with various regulations, please refer to our website at www.fabreeka.com/product-compliance.

World Headquarters
Fabreeka International, Inc.
 PO Box 210
 1023 Turnpike Street
 Stoughton, MA 02072
 Tel: (800) 322-7352
 Tel: (781) 341-3655
 Fax: (781) 341-3983
 E-mail: info@fabreeka.com
www.fabreeka.com

Germany
Fabreeka GmbH Deutschland
 Hessenring 13
 D-64572 Büttelborn
 Tel: 49 - (0)6152-9597-0
 Fax: 49 - (0)6152-9597-40
 E-mail: info@fabreeka.de
www.fabreeka.de

England
ACE Fabreeka UK
 Unit 404 Easter Park
 Haydock Lane
 Haydock WA11 9TH
 Tel: 44 - (0)1942 727440
 Fax: 44 - (0)1942 717273
 E-mail: info@ace-fabreeka.com
www.fabreeka.co.uk

Taiwan
Fabreeka International, Inc.
 PO Box 1246
 Tainan 70499
 Taiwan
 Tel: 886-935 273732
 E-mail: info@fabreeka.tw
www.fabreeka.com.cn